

Technical Data Sheet

High Density Poly-Ethylene for General Purpose applications

Property	Value	Unit
Tensile Strength at Yield in MD	30	МРа
Tensile Strength at Yield in TD	28	МРа
Tensile Strength at Break in MD	60	МРа
Tensile Strength at Break in TD	55	МРа
Elongation at Break in MD	400	%
Elongation at Break in TD	550	%

Note:

The above values are measured for 20 μ film

www.shouman.com



8 El Gaish Street Mansoura - Egypt



info@shouman.com www.shouman.com



+2.050.2.300.200 +2.050.2.300.600